

51. A method according to claim 50 wherein the components of the mix are present in the quantities:

Cement	375 kg/m ³
PUR	250 kg/m ³
Bulking agent	250 kg/m ³
Waterproofing agent (Hydrophobe)	0.1-0.3% w/w cement
Flowing agent (Airalon)	0.03-0.06% w/w cement
Water	200 l/m ³

52. A method according to claim 50 wherein the components of the mix are present in the quantities:

Cement	300 kg/m ³
PUR	327 kg/m ³
Waterproofing agent (Hydrophobe)	0.1-0.3% w/w cement
Flowing agent (Airalon)	0.03-0.06% w/w cement
Water	373 l/m ³

53. A PUR building material obtainable by a method of any of claims 41 to 52.

54. A method of preparing a construction element comprising:

- a) preparing a mould sized to reflect the intended dimensions of the finished board;
- b) introducing a PUR building material according to claim 53 into the mould;
- c) curing the formed board; and
- d) separating the mould and the construction element.